

CRA GUIDE TO SELECTION OF STAINLESS STEELS

Alloy Family	Alloy Type	API Category	Trade Names	UNS Number	Chemical Composition									PREN	API Grade	0.2% Yield Str. (ksi)		Tensile Str. (ksi)	Elong. (%)		CVN Impact (ft-lbs)	Hardness	NACE MR0175/ISO 15156		Alloy Family
					max. wt % or range, unless otherwise indicated											long. at room temperature				trans. at 14F	(HRC)	H ₂ S Limits			
					C	CR	Ni	Mo	Cu	Ti	V	W	N			min.	max.	min.	min.		min.	max.	Tables	Sour Service Limits	
Martensitic Stainless Steel	13 Chrome	5CT 13Cr L80	13CR 420 Mod 13Cr L80	S42000	0.15 to 0.22	12.0 to 14.0	0.5	—	0.25	—	—	—	—	12 to 14	80	80	95	95	function of specimen size	function of wall thickness	23	A.19	H ₂ S ≤ 1.5 psi, pH ≥ 3.5		
	Modified 13 Chrome	N/A	13CRM	N/A	0.03	11.0 to 14.0	4.0 to 6.0	0.2 to 1.2	—	—	—	—	—	12 to 18	80	80	95	90	function of specimen size and strength	29 29 29/30	27 28 32	not recommended for sour service			
			HP1	N/A	0.04	12.0 to 14.0	3.5 to 4.5	0.8 to 1.5	—	—	—	—	—	15 to 19	110	100	140	115							
	Super 13 Chrome	5CRA Group 1 13-5-2 PSL 1 & 2	13CRS CR13S	S41426	0.03	11.5 to 13.5	4.5 to 6.5	1.5 to 3.0	—	0.01 to 0.5	0.5	—	—	16 to 23	80 95 110	80 95 110	95 105 140	90 105 115	function of specimen size and strength	29 29 29/30	27 27 32	A.19	H ₂ S ≤ 1.5 psi, pH ≥ 3.5 110 Gr. not recommended for sour service		
		5CRA Group 1 13-5-2 PSL 1	S13CR	S41425	0.05	12 to 15	4.0 to 7.0	1.5 to 2.0	0.03	—	—	—	0.06 to 0.12	17 to 22	80 95 110	80 95 110	95 105 140	90 105 115	function of specimen size and strength	29 29 29/30	27 28 32	A.18	H ₂ S ≤ 1.5 psi, pH ≥ 3.5 110 Gr. not recommended for sour service		
			SCR13	S41427	0.03	11.5 to 13.5	4.5 to 6.0	1.5 to 2.5	—	0.01 to 0.5	0.1 to 0.5	—	—	16 to 22	80 95 110	80 95 110	95 105 140	90 105 115	function of specimen size and strength	29 29 29/30	27 29 32	A.21	1.5 psi H ₂ S, pH ≥ 3.5, Cl ≤ 6 g/l 110 Gr. not recommended for sour service		
			HP2	N/A	0.04	12.0 to 14.0	4.5 to 5.5	1.8 to 2.5	—	—	—	—	—	18 to 22	80 95 110	80 95 110	95 105 140	90 105 115	function of specimen size and strength	29 29 29/30	27 28 32	not recommended for sour service			
	15 Chrome	N/A	15 Cr	S42500	0.08 to 0.2	14.0 to 16.0	1.0 to 2.0	0.3 to 0.7	—	—	—	—	0.2	15 to 18	N/A	80	95	90			22	A.19	H ₂ S ≤ 1.5 psi, pH ≥ 3.5		
			UHP-15CR Super 15Cr	N/A	0.04	14.0 to 16.0	6.0 to 7.0	1.8 to 2.5	1.5	—	—	—	—	20 to 24	125	125	150	135	function of specimen size and strength		37		not recommended for sour service		
	17 Chrome	N/A	17CRS Super 17Cr	N/A	0.03	16.0 to 18.0	4.0 to 5.5	2.0 to 3.0	2.0 to 3.0	—	0.1	—	—	23 to 28	125	125	145	130	function of specimen size and strength		38		not recommended for sour service		



CRA GUIDE TO SELECTION OF STAINLESS STEELS

Alloy Family	Alloy Type	API Category	Trade Names	UNS Number	Chemical Composition									PREN	API Grade	0.2% Yield Str. (ksi)		Tensile Str. (ksi)	Elong. (%)		CVN Impact (ft-lbs)	Hardness	NACE MR0175/ISO 15156		Alloy Family
					max. wt % or range, unless otherwise indicated											long. at room temperature				trans. at 14F	(HRC)	H ₂ S Limits			
					C	CR	Ni	Mo	Cu	Ti	V	W	N			min.	max.	min.	min.		min.	max.	Tables	Sour Service Limits	
Duplex Stainless Steel	22 Chrome Duplex	5CRA Group 2 22-5-3 PSL 1 & 2	22Cr 2205	S31803	0.03	21.0	4.5	2.5	—	—	—	—	0.08	35 to 40	65 75 110	65	90	90	25%	function of strength and wall thickness	26	26	A.24 (annealed)	H ₂ S ≤ 1.5 psi, Temps ≤ 450F	
						to 23.0	to 6.5	to 3.5	—	—	—	—	to 0.20										125		140
	25 Chrome Duplex	5CRA Group 2 25-7-3 PSL 1 & 2	25Cr 2507	S31260	0.03	24.0	5.5	2.5	0.2	—	—	0.10	0.10	37 to 40	125 140	125	150	130	10%	function of strength and wall thickness	36	38	A.25 (cold worked)	H ₂ S ≤ 0.3 psi 140 Gr. not recommended for sour service	
						to 26.0	to 7.5	to 3.5	to 0.8	—	—	to 0.50	to 0.30												140
	Super Duplex	5CRA Group 2 25-7-4 PSL 1 & 2	SAF 2507	S32750	0.03	24.0	6.0	3.0	—	—	—	—	0.24	40 to 45	80	80	105	110	20%	function of strength and wall thickness	28	30	A.24 (annealed)	H ₂ S ≤ 3.0 psi, Temps ≤ 450F	
						to 26.0	to 8.0	to 4.0	—	—	—	to 0.32	90												105
						25CRS Z 100	S32760	0.03	24.0	6.0	3.0	0.5	—	—	0.50	0.20	40	110	110	140	125	10%	36	38	A.25 (cold worked)
	25CRW	S39274	0.03	24.0	6.0	2.5	0.2	—	—	1.5	0.24	40	125	125	150	130	10%								
							to 26.0	to 8.0	to 3.5	to 0.8	—	—	to 2.5	to 0.32	45	140	140	160	145	9%					



CRA GUIDE TO SELECTION OF NICKEL ALLOYS

Alloy Family	Alloy Type	API Category	Trade Names	UNS Number	Chemical Composition										PREN	API Grade	0.2% Yield Str. (ksi)		Tensile Str. (ksi)	Elong. (%)	CVN Impact (ft-lbs)	Hardness	NACE MR0175/ISO 15156		Alloy Family
					max. wt % or range, unless otherwise indicated												long. at room temperature			trans. at 14F	(HRC)	H ₂ S Limits			
					Cr	Ni	Fe	Mo	Co	Cu	Ti	Nb+Ta	W	AL			min.	max.	min.	min.	min.	max.	Tables	Sour Service Limits	
Solid Solution Nickel Base Alloys	28 Chrome	5CRA Group 3 27-31-4 PSL 1 & 2	28 Chrome Alloy 28	No8028	26.0 to 28.0	29.5 to 32.5	bal.	3.0 to 4.0	—	0.6 to 1.4	—	—	—	—	36 to 41	110 125 140	110 125 140	140 150 160	115 130 145	11% 10% 9%	function of strength & wall thickness	33 35 38	A.14	no limit ≤270F, refer to table for temperatures up to 450F 140 Gr. not recommended for sour service	
	2535	5CRA Group 3 25-32-3 PSL 1 & 2	2535	No8535	24.0 to 27.0	29.0 to 36.5	bal.	2.5 to 4.0	—	1.5	—	—	—	32 to 40											
	2035	5CRA Group 3 22-35-4 PSL 1 & 2	2035	No8135	20.5 to 23.5	33.0 to 38.0	bal.	4.0 to 5.0	—	0.7	—	—	0.2 to 0.8	34 to 41											
	825	5CRA Group 4 21-42-3 PSL 1 & 2	825 2242	No8825	19.5 to 23.5	38.0 to 46.0	bal.	2.5 to 3.5	—	1.5 to 3.0	0.6 to 1.2	—	—	0.2	28 to 35										
	G3	5CRA Group 4 22-50-7 PSL 1 & 2	G3	No6985	21.0 to 23.5	bal.	18.0 to 21.0	6.0 to 8.0	5.0	1.5 to 2.5	—	0.50	1.5	—	41 to 50	110 125 140	110 125 140	140 150 160	115 130 145	11% 10% 9%	function of strength & wall thickness	35 37 38	A.14	no limit ≤300F, refer to table for temperatures up to 450F 140 Gr. not recommended for sour service	
	G2	5CRA Group 4 25-50-6 PSL 1 & 2	G2	No6975	23.0 to 26.0	47.0 to 52.0	bal.	5.0 to 7.0	—	0.7 to 1.2	0.7 to 1.5	—	—	—	40 to 49										
	2550		2550 CRA 2550E	No6255	23.0 to 26.0	47.0 to 52.0	bal.	6.0 to 9.0	—	1.2	0.69	—	3.0	—	43 to 56										
	G50	5CRA Group 4 20-54-9 PSL 1 & 2	G50 Alloy 050	No6950	19.0 to 21.0	50.0 min	15.0 to 20.0	8.0 to 10.0	2.5	0.5	—	0.50	1.0	—	45 to 54	110 125 140	110 125 140	140 150 160	115 130 145	11% 10% 9%	function of strength & wall thickness	35 37 38	A.14	no limit ≤400F, refer to table for temperatures up to 450F	
	C276	5CRA Group 4 15-60-16 PSL 1 & 2	C276	N10276	14.5 to 16.5	bal.	4.0 to 7.0	15.0 to 17.0	2.5	—	—	—	3.0 to 4.5	—	69 to 80										
	C22	N/A	Alloy 22	No6022	20.0 to 22.5	bal.	2.0 to 6.0	12.5 to 14.5	2.5	—	—	—	2.5 to 3.5	—	65 to 76										

